

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : A61K 6/00		(11) International Publication Number: WO 99/45888
A2		(43) International Publication Date: 16 September 1999 (16.09.99)
(21) International Application Number: PCT/US99/05176		(81) Designated States: AU, CA, JP, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>Without international search report and to be republished upon receipt of that report.</i>
(22) International Filing Date: 10 March 1999 (10.03.99)		
(30) Priority Data: 60/077,378 10 March 1998 (10.03.98) US 60/077,555 11 March 1998 (11.03.98) US 60/088,866 11 June 1998 (11.06.98) US 60/091,527 2 July 1998 (02.07.98) US 09/133,582 13 August 1998 (13.08.98) US		
(71) Applicant: JENERIC PENTRON INCORPORATED [US/US]; 53 North Plains Industrial Road, Wallingford, CT 06492 (US).		
(72) Inventors: BRODKIN, Dmitri; 75 Hebert Terrace, West Orange, NJ 07052 (US). PANZERA, Carl; 7 Huntsman Lane, Belle Mead, NJ 08502 (US). PANZERA, Paul; 1 Middleton Drive, Mt. Holly, NJ 08060 (US). PRUDEN, Jana, N.; 70 Dehart Drive, Belle Mead, NJ 08502 (US). KAISER, Lisa; 1201 Holly Court, Monmouth Junction, NJ 08852 (US). BRIGHTLY, Richard; 14 Peachtree Court, South Brunswick, NJ 08852 (US).		
(74) Agent: REIMER, Leah, M.; Cantor Colburn LLP, 88 Day Hill Road, Windsor, CT 06095 (US).		
(54) Title: LOW FUSING DENTAL PORCELAINS CONTAINING FINE-GRAINED LEUCITE		
(57) Abstract A dental porcelain composition, comprising a glassy matrix and leucite crystallites embedded therein, and having maturing temperatures in the range from about 600 °C to about 885 °C and CTEs in the range from about 11 to about 19, more preferably in the range from about 11.5 to about 18, and most preferably in the range from about 12 to about 17.5 x 10 ⁻⁶ /°C (measured from 25 °C to 500 °C). The tetragonal leucite is preferably both fine-grained (i.e., having average diameters of less than about 7 microns) and uniformly-sized. Preferably, the average diameters are less than about 1 to about 3 microns.		

dto

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

LOW FUSING DENTAL PORCELAINS CONTAINING FINE-GRAINED LEUCITE

Background of the Invention

1. Field of the Invention

The present invention relates to feldspathic leucite-containing dental porcelain compositions for dental restorations. More particularly, this invention relates to low-fusing dental porcelain compositions useful in the preparation and repair of dental restorations such as porcelain-fused-to-metal restorations, all-ceramic restorations, inlays, onlays, and veneers, wherein the leucite is fine-grained.

2. Brief Description of the Related Art

Porcelain dental restorations, such as crowns, bridges, and the like are highly favored because the porcelains provide strength, wear resistance, and favorable aesthetics. Older porcelain restorations generally comprise at least one porcelain layer on a metal framework, commonly known as porcelain-fused-to-metal ("PFM") restorations. Typically, PFM restorations are fabricated by applying a dental porcelain powder in aqueous slurry to a metal alloy framework, then firing the porcelain at high temperature to form a tight, impervious porcelain layer having the appearance of natural dentition. Those skilled in the art recognize that it is important that the firing temperature of the porcelain be at least 100° C below the solidus temperature of the

-2-

alloy used as the metal framework, to prevent melting or distortion of the metal framework. It is further important that the coefficient of thermal expansion (CTE) of the porcelain be only slightly less than that of the metal so that no cracks are produced in the porcelain layer due to thermal expansion mismatch stress occurring during firing and cooling down. Metal alloys heretofore employed in the manufacture of dental restorations have typically possessed moderately high coefficients of thermal expansion ranging from about $13 \times 10^{-6} / ^\circ\text{C}$ to about $17.5 \times 10^{-6} / ^\circ\text{C}$, with the exception of titanium, which has a coefficient of thermal expansion of about $9 \times 10^{-6} / ^\circ\text{C}$.

In commonly assigned U.S. Application Ser. No. 08/532,179 filed September 22, 1995, the contents of which are incorporated by reference herein, a dental porcelain composition is described which is amorphous, i.e., single phase, and which possesses a moderately high coefficient of thermal expansion closely matching those of conventional alloys and some ceramics heretofore employed in the manufacture of dental restorations. This composition is advantageously applied to such conventional alloys to provide an extremely smooth, fused glassy surface on the resulting dental restoration

Newer restorations, however, generally comprise a ceramic core in place of the traditional metal, with at least one additional porcelain layer. These are commonly referred to as "all-ceramic" systems, and can provide even better aesthetics than the metal-porcelain systems. Among all-ceramic systems, high strength porcelains provide a more natural translucency and therefore much improved aesthetics. Dental ceramics exhibit a wide range of coefficients of thermal expansion, from as low as about $8 \times 10^{-6} / ^\circ\text{C}$ (e.g., alumina) to as high as about $18 \times 10^{-6} / ^\circ\text{C}$ (e.g., some leucite-reinforced ceramics).

Among the commercially-available all-ceramic systems, many are based on pressable, high-strength feldspathic porcelains, for example pressable leucite-reinforced porcelains commercially available under the trade name "OPC[®]" from Jeneric[®]/Pentron[®], Inc. (Wallingford, CT). These feldspathic glass-ceramics comprise from about 40% to 50% of a discontinuous, evenly dispersed, tetragonal potassium leucite phase, which imparts strength to the dental restoration. Leucite is a crystalline

-3-

potassium aluminum silicate ($K_2O \cdot Al_2O_3 \cdot 4SiO_2$) which ordinarily has a tetragonal crystal structure at room temperature. Use of tetragonal leucite, also known as "low leucite", is described for reinforcement of feldspathic dental porcelains in U.S. Patent No. 3,052,982 to Weinstein et al., U.S. Patent No. 4,604,366 to Kacicz et al., U.S.

5 Patent No. 4, 798,536 to Katz, and U.S. Patent No. 5,614,330 to Panzera, the entire contents of the foregoing patents being incorporated herein by reference. While well-suited for their intended purposes, prior art porcelains for all-ceramic restorations are available in a limited range of maturing temperatures and CTEs, and contain leucite having at least some coarse-grained morphology, that is, a distribution of grain sizes
10 wherein at least a fraction of the grains are greater than about 10 microns, or even greater than about 20 microns. Such coarse-grained leucite can wear away the opposing natural dentition in the mouth.

There accordingly remains a need in the art for high-strength porcelain systems wherein the maturing temperature is low enough to match that of commercially-
15 available metal frameworks, including gold alloys and porcelain cores, and even more advantageously, wherein the CTE may be adjusted to match a range of metal substructure or all ceramic cores. There particularly remains a need for high-strength porcelain systems having low maturing temperatures, yet higher CTEs, and having a fine-grained leucite crystal structure for reducing wear of the opposing natural
20 dentition. Such porcelains must further be simple and inexpensive to manufacture.

Summary of the Invention

The above-described drawbacks and deficiencies of the prior art are alleviated by the low-fusing dental porcelain compositions of the present invention comprising a glassy matrix and tetragonal leucite dispersed therein, and having maturing
25 temperatures in the range from about 600 °C to about 885 °C, more preferably in the range from about 650 °C to about 875 °C and most preferably in the range from about 675 °C to about 870 °C, and CTEs in the range from about 11 to about 19, more preferably in the range from about 11.5 to about 18, and most preferably in the range from about 12 to about 17.5 x 10⁻⁶/°C (measured from 25 °C to 500 °C). The

-4-

tetragonal leucite in accordance with the present invention is preferably both fine-grained (i.e, having average diameters of less than about 7 microns) and uniformly-sized. The compositions are described in more detail below.

- In one embodiment of the method of the present invention, a porcelain frit comprising fine grain sized tetragonal leucite is combined with at least one frit having a very low maturing temperature in order to produce the porcelain of the present invention. In another embodiment of the method of the present invention, the fine grain sized tetragonal leucite is crystallized from a single glassy frit in the initially amorphous glass by heat-treatment of this starting amorphous glass powder.
- 10 The porcelains in accordance with the present invention are especially suitable for use in dental restorations as overlay porcelains in combination with both dental alloys and leucite-reinforced core porcelains such as those available from Jeneric®/Pentron® under the trademark OPC®. The restorations thus produced are both aesthetic and forgiving to natural dentition, in that the presence of fine-grained leucite
- 15 results in less wear of the opposing dentition.

Detailed Description of the Invention

- The present invention is directed to a low-fusing dental porcelain comprising a glassy matrix and tetragonal leucite, and having maturing temperatures in the range from about 600 °C to about 885 °C, preferably in the range from about 650 °C to about
- 20 875 °C, and most preferably in the range from about 675 °C to about 870 °C, and coefficients of thermal expansion in the range from about 11 to about 19, more preferably in the range from about 11.5 to about 18, and most preferably in the range from about 12 to about $17.5 \times 10^{-6}/^{\circ}\text{C}$ (measured from 25 °C to 500 °C).

- The tetragonal leucite in accordance with the present invention is preferably
- 25 both fine-grained and uniformly-sized, in order to prevent wear to the opposing dentition. By "fine-grained" is meant leucite crystallites having average diameters of less than about seven microns, preferably less than about five microns, and most preferably less than about two to three microns. Individual leucite grains having greater diameters may of course be present, but the presence of such grains is preferably

-5-

minimized. As used herein, "diameters" refers to the longest single dimension of the crystallite, regardless of the shape of the crystallite.

The amount of leucite present in the glassy matrix is effective to achieve maturing temperatures in the range from about 600 °C to about 875 °C and coefficients of thermal expansion in the range from about 11 to about $19 \times 10^{-6}/^{\circ}\text{C}$ (measured from 25 °C to 500 °C), and is empirically determined by means known in the art, depending on the size and distribution of the tetragonal leucite, the composition of the glassy matrix, the desired maturing temperature and coefficient of thermal expansion, and the intended use of the porcelain (e.g., as a core or as an overlay porcelain). Generally, the leucite is present in an amount in the range from about 5% to about 65% by weight of the total composition, and preferably in the range from about 5% to about 40% by weight of the total composition. As is mentioned below, inclusion of cesium in the glass composition will minimize the amount of leucite required in order to achieve a higher coefficient of thermal expansion.

In one embodiment of the method of manufacture of the present invention, a first porcelain component comprising fine grain sized tetragonal leucite is combined with at least one second porcelain component having a very low maturing temperature, for example in the range from about 600 °C to about 760 °C. The composition of the first porcelain component and the at least one second porcelain component is such that combination of the first and second porcelain compositions yields the compositions given in the Tables below. In general, use of at least two porcelain components, or frits, allows greater control in fine-tuning the coefficient of thermal expansion and maturing temperature of the porcelain composition.

The tetragonal leucite for the first porcelain component may be synthesized by means known in the art, for example by volume crystallization. Thus a mixture of powdered metal oxides or carbonates in the appropriate proportions are blended, for example by ball milling for one to three hours. Nucleation agents such as P_2O_5 , PbO , combinations of MgO , ZnO , TiO_2 and the like are optionally added to the metal oxides and/or carbonates before blending in order to control nucleation density. The blended powders are then fused to form a glass melt, the glass is quenched (in water or by other

-6-

means,) and then heated to an elevated temperature (e.g., 950 -1100 °C) for approximately one to six hours, allowing the formation and growth of the crystalline leucite. Alternatively, the powders are fused to form a glass, then directly cooled to the crystallization temperature without intermediate quenching. After leucite formation, 5 the material is then quenched, crushed, and reduced to a fine powder. Volume crystallization is known in the art, being described for example in U.S. Patent No. 4,455,383 to Panzera and U.S. Patent No. 4,798,536 to Katz, the contents of which patents are incorporated by reference herein.

Alternatively, the leucite-containing porcelain component may be formed by 10 surface crystallization, wherein a mixture of powdered metal oxides or carbonates in the appropriate proportions (and optional nucleation agents) are blended, for example by ball milling for one to three hours. The powders are then fused to form a glass melt, which is quenched in water or by other means. The quenched glass is then milled to a powder before subjecting the powder to heat treatment in order to form crystallized 15 leucite.

In a second embodiment of the method of the present invention, the dental porcelains are formed by volume crystallization of fine grained leucite from a single porcelain composition as described in connection with the first porcelain component above.

20 Compositional ranges for the fine grained leucite porcelains in accordance with the present invention are shown in the Table below.

-7-

Comp onent	Range							
	1	2	3	4	5	6	7	8
SiO ₂	40-65	40-65	40-65	58-65	58-65	57-66	57-66	57-66
Al ₂ O ₃	6-12	6-13	6-12	6-12	6-13	7-13	7-13	7-13
K ₂ O	5.5-10.5	5-15	5-15	5.5-18	5-15	7-14.5	7-18	7-18
Na ₂ O	6-12	6-12	6-12	7-12	7-12	7-12	4-12	7-12
Li ₂ O	1-3	1-3	0-3	1.5-3	1.5-3	0.3-3	0.5-3	0-3
B ₂ O ₃	0.5-4	0.5-4	0-4	0.5-4	0.5-4	*	0-1	0-4
BaO	0-2	0-2	0-2	0-2	0-2	0-2	0-2	0-2
CaO	0.8-2.5	0.8-2.5	0-3	1.2-2.5	1.2-2.5	0-3	0-3	0-3
MgO	0-7	0-7	0-4	0-7	0-7	0-7	0-7	0-7
Cs ₂ O	0-5	0-5	0-5	0-3	0-3	0-5	0-5	0-5
F	0-2	0-2	0-2	0-2	0-2	0-4	0-4	0-4
P ₂ O ₅	0-3	0-3	0-3	0-3	0-3	0-3	0-3	0-3
CeO ₂	0.1-0.8	0.1-0.8	0-1	0.1-2	0.1-2	0-1	0-1	0-1
Sb ₂ O ₃	0-0.5	0-0.5	0-1	0.1-1	0.1-1	0-1	0-0.5	0-1
Acidic flux ¹	0.5-4	0.5-4	0.8-4	0.5-4	0.5-4	0.8-4.0	0.8-4	0.8-4
Alkaline flux ²	7-15	7-15	6-15	8.5-15	8.5-15	7.3-15	4.5-15	7-15
Additives ³	0.5-40	0.5-40	0.5-40	0-5	0-5	0-5	0-5	0-5

*Component excluded from composition except as unavoidable and unintended contaminant

¹B₂O₃ + F + P₂O₅

²Li₂O + Na₂O

³Pigments, opacifying agents, fluorescing agents

-8-

The properties of the porcelain components and compositions can be adjusted by applying well known principles. For example, the coefficient of thermal expansion can be increased, if desired, by increasing the leucite content, and by decreasing the proportion of SiO_2 and/or increasing the proportion of the alkali metal oxides. Addition
5 of small quantities of Cs_2O , wherein the molar ratio of $\text{Cs}_2\text{O}/\text{K}_2\text{O}$ is less than 0.1, may significantly increase the expansion of the resulting porcelain. Accordingly, the leucite content is adjusted downward in order to obtain the same CTE. The presence of the acidic fluxes, that is, B_2O_3 , P_2O_5 or F or their combination wherein $\text{B}_2\text{O}_3 + \text{F} + \text{P}_2\text{O}_5 =$
10 0.5- 4% or -.8- 4% by weight is necessary to attain the requisite crystallization parameters and/or to lower the maturing temperatures. Alkaline fluxes refers to the total quantity of $\text{Li}_2\text{O} + \text{Na}_2\text{O}$.

The porcelain in accordance with the present invention comprises or may further comprise other additives known in the art, such as opacifiers, pigments (e.g., chromates, vanadates, and manganates, and the like) and fluorescing agents (e.g.,
15 cerium oxide, 0.5-2% Tb_2O_3 , 0- 0.4% Y_2O_3 , and the like).

The following compositions (percent by weight) are exemplary of the compositions of the dental porcelains of the present invention, showing both the intended use of the composition and whether it was derived from a single frit or two frits:

	Component	Ex. 1 (two frit)	Ex. 2 (two frit)	Ex. 3 (two frit)	Ex. 4 (two frit)	Ex. 5 (single frit)	Ex. 6 (single frit)
	SiO ₂	62.0	61.5	64.2	62.7	63.2	64.4
	Al ₂ O ₃	11.7	9.7	9.5	10.1	9.7	9.0
	K ₂ O	15.8	14.0	13.5	11.0	15.3	13.8
5	Na ₂ O	4.7	6.6	8.3	10.3	7.5	8.2
	Li ₂ O	2.6	2.2	1.4	1.2	1.2	1.2
	B ₂ O ₃	0.50	0.9	0	1.51	0	0
	BaO	0	0	0	0	0	0
	CaO	1.7	1.7	1.1	1.6	1.1	1.2
10	MgO	0.8	0.7	1.0	0.9	1.1	1.1
	F	0.5	0.9	1.8	1.2	1.8	2.0
	B ₂ O ₃ + F + P ₂ O ₅	1.0	1.8	1.8	2.8	1.8	2.0
	Cs ₂ O	0	2.1	0	0	0	0
15	CTE*	17.5	18.0	13.7	13.7	17.5	13.8
	Maturing T, °C	857	816	750-760	750-760	760	737
	Wt. % leucite	40	30	7	7	40	10

20 * x 10⁻⁶/ °C measured over 25 °C to 470 °C

The above compositions were calculated based on starting batch compositions. Actual fluorine content may therefore be significantly lower due to volatilization losses during melting. The exact percentages of other components such as Li₂O and B₂O₃ may also deviate slightly from these calculated values. Li₂O values were obtained by adding to the amount of Li₂O a factor calculated by multiplying the weight percent of fluorine by 16 and dividing by 38. Other components may or may not be present depending on the particular use and physical requirements of the porcelain. Examples 1, 2, 3, and 4

-10-

are formulated using the two-frit method, while Examples 5 and 6 were obtained using surface-driven crystallization of leucite from the ground glass powder of a single frit.

The quantity of leucite in Examples 1 and 2 were measured, and found to be approximately 40% by weight (Example 1) and 30% by weight (Example 2). One of
5 ordinary skill in the art would therefore expect the CTE for Example 1 to be higher than that for Example 2, based in the increased amount of leucite. However, the measured CTEs are 17.5 and 18, respectively. Examples 1 and 2 thus illustrate the principle whereby increasing the weight percent of Cs_2O and the molar ratio of $\text{Cs}_2\text{O}/\text{K}_2\text{O}$ to less than 0.1 leads to a composition having less leucite, but a CTE comparable to, or higher
10 than, a composition where more leucite is present. Since even fine-grained leucite wears away opposing dentition, the composition of Example 2 provides particularly low wear of opposing dentition.

The porcelains of Examples 1, 2 and 5 are compatible with OPC[®] cores and type IV gold alloys having expansions in the range from $16\text{-}17.5 \times 10^{-6}/^\circ\text{C}$. Porcelains of
15 Examples 3, 4, and 6 are compatible with non-precious alloys, for example alloys having CTEs in the range from $13.6\text{-}14.9 \times 10^{-6}/^\circ\text{C}$ compatible with the SYNSPART[™] Porcelain System and yellow gold alloys having coefficients of thermal expansion of about $14 \times 10^{-6}/^\circ\text{C}$, and all-ceramic cores comprising cubic leucite. The exact CTEs of porcelains of course depend on the range over which the measurements are made. For
20 example, the CTEs for Examples 3 and 4 are about 12.4 (measured over $25\text{-}400^\circ\text{C}$), about 12.7 (measured over $25\text{-}430^\circ\text{C}$), about 13.7 (measured over $25\text{-}470^\circ\text{C}$), and about 13.5 (measured over $25\text{-}500^\circ\text{C}$). Thus, the porcelains of Examples 3 and 4 are matched to alloys having expansions in the range from about $13.6\text{-}14.9 \text{ ppm}/^\circ\text{C}$, as well as all-ceramic cores having compatible thermal expansions.

25 In one embodiment, the porcelain composition of the present invention is fused to a metal alloy framework or all-ceramic core to provide a coating thereon. Suitable alloys include those known in the art having a coefficient of thermal expansion in the range from about 13.2 to about $14.9 \times 10^{-6}/^\circ\text{C}$, or in the range from about 16 to about $17.5 \times 10^{-6}/^\circ\text{C}$. Suitable all-ceramic cores include, but are not limited to cores available
30 under the trade name OPC[™] from Jeneric/Pentron, Wallingford, CT; under the trade

-11-

name EMPRESS™, from Ivoclar; and under the trade name CERPRESS™, from the Dillon, Co., Cranston, RI. Such restorations commonly have multiple porcelain layers in order to simulate natural teeth, and the porcelain of this invention may be used in any one or a combination of these layers, although it is preferably used as an overlayer. The
5 porcelain layers are applied in the conventional manner, that is, in the form of a paste of the porcelain powder in water over the framework, shaping to the desired shape, and then firing.

In another embodiment, the porcelain is used to fabricate inlays, onlays, or veneers to replace amalgam, gold, or other porcelains. In this embodiment, the
10 porcelain powder in accordance with the present invention is built on a refractory die (for example, the refractory die available from Jeneric/Pentron Inc., Wallingford, CT under the trade name SYNVEST™) in the form of an aqueous slurry, and then fired to an appropriate temperature to effect maturation and maturing of the porcelain.

While various descriptions of the present invention are described above, it
15 should be understood that various features can be used singly or in any combination thereof. Therefore, this invention is not to be limited to only the specifically preferred embodiment depicted herein. Further, it should be understood that variations and modifications within the spirit and scope of the invention may occur to those skilled in the art to which the invention pertains. Accordingly, all expedient modifications ready
20 attainable by one versed in the art from the disclosure set forth herein that are within the scope and spirit of the present invention are to be included as further embodiments of the present invention. The scope of the present invention is accordingly defined as set forth in the appended claims.

What is claimed is:

-12-

CLAIM 1. A composition for the manufacture of a dental porcelain, comprising
40-65% SiO₂, 6-13% Al₂O₃, 5.5-15% K₂O, 6-12% Na₂O, 0.5-3% Li₂O, 0-4%
B₂O₃, 0-2% F, and 0-3% P₂O₅ by weight of the total composition, wherein the weight
percent of (F + B₂O₃ + P₂O₅) is in the range from 0.8-4.0 and the weight percent of
5 (Li₂O + Na₂O) is in the range from 6-15, and wherein the porcelain comprises
a glassy matrix phase and a leucite crystallite phase, wherein the leucite phase
comprises from about 5 to about 65% by weight of the total composition and the leucite
crystallites have average diameters of less than about 7 microns; and further wherein
the porcelain has a maturing temperature in the range from about 600 °C to
10 about 885 °C and a coefficient of thermal expansion in the range from about 11 to
about 19 x 10⁻⁶/°C (measured from 25 °C to 500 °C).

CLAIM 2. The composition of claim 1, further comprising at least one of
0-2% BaO, 0-3% CaO, 0-4% MgO, 0-5% Cs₂O, 0-1% CeO₂, or 0-1% Sb₂O₃.

CLAIM 3. The composition of claim 2, comprising
62.7% SiO₂, 10.11% Al₂O₃, 11.0% K₂O, 10.3% Na₂O, 1.2% Li₂O, 1.5% B₂O₃,
1.6% CaO, 0.9% MgO, and 1.2% F.

-13-

CLAIM 4. A composition for the manufacture of a dental porcelain, comprising
40-65% SiO_2 , 6-12% Al_2O_3 , 5.5-10.5% K_2O , 6-12% Na_2O , 1-3% Li_2O , 0.5-4%
 B_2O_3 , 0.8-2.5% CaO , 0-2% F , 0-3% P_2O_5 , and 0.1-0.8% CeO_2 by weight of the total
composition, wherein the weight percent of ($\text{F} + \text{B}_2\text{O}_3 + \text{P}_2\text{O}_5$) is in the range from 0.5-
5 4.0 and the weight percent of ($\text{Li}_2\text{O} + \text{Na}_2\text{O}$) is in the range from 7-15, and wherein the
porcelain comprises

a glassy matrix phase and a leucite crystallite phase, wherein the leucite phase
comprises from about 5 to about 65% by weight of the total composition and the leucite
crystallites have average diamters of less than about 7 microns; and further wherein

10 the porcelain has a maturing temperature in the range from about 600 °C to
about 885 °C and a coefficient of thermal expansion in the range from about 11 to
about $19 \times 10^{-6}/^\circ\text{C}$ (measured from 25 °C to 500 °C).

CLAIM 5. A composition for the manufacture of a dental porcelain, comprising
40-65% SiO_2 , 6-13% Al_2O_3 , 5-15% K_2O , 6-12% Na_2O , 1-3% Li_2O , 0.5-4%
 B_2O_3 , 0.8-2.5% CaO , 0-2% F , 0-3% P_2O_5 , and 0.1-0.8% CeO_2 by weight of the total
composition, wherein the weight percent of ($\text{F} + \text{B}_2\text{O}_3 + \text{P}_2\text{O}_5$) is in the range from 0.5-
5 4.0 and the weight percent of ($\text{Li}_2\text{O} + \text{Na}_2\text{O}$) is in the range from 7-15, and wherein the
porcelain comprises

a glassy matrix phase and a leucite crystallite phase, wherein the leucite phase
comprises from about 5 to about 65% by weight of the total composition and the leucite
crystallites have average diamters of less than about 7 microns; and further wherein

10 the porcelain has a maturing temperature in the range from about 600 °C to
about 885 °C and a coefficient of thermal expansion in the range from about 11 to
about $19 \times 10^{-6}/^\circ\text{C}$ (measured from 25 °C to 500 °C).

CLAIM 6. The composition of claims 4 and 5, further comprising at least one of
0-2% BaO , 0-7% MgO , 0-5% Cs_2O , or 0-0.5% Sb_2O_3 .

-14-

CLAIM 7. A composition for the manufacture of a dental porcelain, comprising
58-65% SiO₂, 6-12% Al₂O₃, 5.5-18% K₂O, 7-12% Na₂O, 1.5-3% Li₂O, 0.5-4%
B₂O₃, and 1.2-2.5% CaO, 0-2% F, 0-3% P₂O₅, 0.1-1.0% Sb₂O₃ and 0.1-2% CeO₂ by
weight of the total composition, wherein the weight percent of (F + B₂O₃ + P₂O₅) is in
5 the range from 0.5-4.0 and the weight percent of (Li₂O + Na₂O) is in the range from
8.5-15, and wherein the porcelain comprises
a glassy matrix phase and a leucite crystallite phase, wherein the leucite phase
comprises from about 5 to about 65% by weight of the total composition and the leucite
crystallites have average diameters of less than about 7 microns; and further wherein
10 the porcelain has a maturing temperature in the range from about 600 °C to
about 885 °C and a coefficient of thermal expansion in the range from about 11 to
about 19 x 10⁻⁶/°C (measured from 25 °C to 500 °C).

CLAIM 8. A composition for the manufacture of a dental porcelain, comprising
58-65% SiO₂, 6-13% Al₂O₃, 5-15% K₂O, 7-12% Na₂O, 1.5-3% Li₂O, 0.5-4%
B₂O₃, 1.2-2.5% CaO, 0-2% F, 0-3% P₂O₅, 0.1-1% Sb₂O₃ and 0.1-2% CeO₂ by weight of
the total composition, wherein the weight percent of (F + B₂O₃ + P₂O₅) is in the range
5 from 0.5-4.0 and the weight percent of (Li₂O + Na₂O) is in the range from 8.5-15, and
wherein the porcelain comprises
a glassy matrix phase and a leucite crystallite phase, wherein the leucite phase
comprises from about 5 to about 65% by weight of the total composition and the leucite
crystallites have average diameters of less than about 7 microns; and further wherein
10 the porcelain has a maturing temperature in the range from about 600 °C to
about 885 °C and a coefficient of thermal expansion in the range from about 11 to
about 19 x 10⁻⁶/°C (measured from 25 °C to 500 °C).

CLAIM 9. The composition of claims 7 and 8, further comprising at least one of
0-2% BaO, 0-7% MgO, or 0-3% Cs₂O.

-15-

CLAIM 10. A composition for the manufacture of a dental porcelain, comprising
57-66% SiO₂, 7-13% Al₂O₃, 7-18% K₂O, 4-12% Na₂O, 0.5-3% Li₂O, 0-1%
B₂O₃, and 0-4% F by weight of the total composition, wherein the weight percent of (F
+ B₂O₃ + P₂O₅) is in the range from 0.8-4.0 and the weight percent of (Li₂O + Na₂O) is
5 in the range from 4.5-15, and wherein the porcelain comprises
a glassy matrix phase and a leucite crystallite phase, wherein the leucite phase
comprises from about 5 to about 65% by weight of the total composition and the leucite
crystallites have average diameters of less than about 7 microns; and further wherein
the porcelain has a maturing temperature in the range from about 600 °C to
10 about 885 °C and a coefficient of thermal expansion in the range from about 11 to
about 19 x 10⁻⁶/°C (measured from 25 °C to 500 °C).

CLAIM 11. The composition of claim 10, further comprising at least one of
0-2% BaO, 0-3% CaO, 0-7% MgO, 0-5% Cs₂O, 0-1% Ce₂O, or 0-1% Sb₂O₃.

CLAIM 12. The composition of claim 11, comprising
62.0% SiO₂, 11.7% Al₂O₃, 15.8% K₂O, 4.7% Na₂O, 2.3-3% Li₂O, 0.5% B₂O₃,
1.7% CaO, 0.8% MgO, and 0.5% F by weight of the total composition.

CLAIM 13. The composition of claim 11, comprising
61.5% SiO₂, 9.7% Al₂O₃, 14.0% K₂O, 6.6% Na₂O, 2.2% Li₂O, 0.9% B₂O₃,
1.7% CaO, 0.7% MgO, 0.9% F and 2.1% Cs₂O by weight of the total composition.

-16-

- CLAIM 14. A composition for the manufacture of a dental porcelain, comprising
57-66% SiO₂, 7-13% Al₂O₃, 7-14.5% K₂O, 7-12% Na₂O, 0.3-3% Li₂O, 0-2%
BaO, being devoid of B₂O₃ by weight of the total composition, wherein the weight
percent of (Li₂O + Na₂O) is in the range from 7.3-15, and wherein the porcelain
5 comprises
a glassy matrix phase and a leucite crystallite phase, wherein the leucite phase
comprises from about 5 to about 65% by weight of the total composition and the leucite
crystallites have average diameters of less than about 7 microns; and further wherein
the porcelain has a maturing temperature in the range from about 600 °C to
10 about 885 °C and a coefficient of thermal expansion in the range from about 11 to
about 19 x 10⁻⁶/°C (measured from 25 °C to 500 °C).
- CLAIM 15. The composition of claim 14, wherein
the composition further comprises at least one of 0-3% CaO, 0-7% MgO, 0-4%
F, 0-1% CeO₂, or 0-1% Sb₂O₃.
- CLAIM 16. The porcelain of claim 14, wherein the composition comprises
64.2% SiO₂, 9.5% Al₂O₃, 13.5% K₂O, 8.3% Na₂O, 1.4% Li₂O, 1.1% CaO, and
1.0% MgO, and 1.8% F by weight of the total composition.
- CLAIM 17. The composition of claims 1-16, wherein
the average leucite crystallite diameter is less than about 3 microns.
- CLAIM 18. The composition of claims 1-16, wherein
the average leucite crystallite diameter is between about 1 and about 3 microns.
- CLAIM 19. A glassy powder for the manufacture of the porcelain of claim 14
comprising
64.4% SiO₂, 9.0% Al₂O₃, 13.8% K₂O, 8.2% Na₂O, 1.2% Li₂O, 1.2% CaO, 1.1%
MgO, and 2.0% F by weight of the total composition.

-17-

CLAIM 20. A composition for the manufacture of a dental porcelain, comprising
57-66% SiO₂, 7-13% Al₂O₃, 7-18% K₂O, 7-12% Na₂O, 0-3% Li₂O, 0-4% B₂O₃
and 0-2% F by weight of the total composition, wherein the weight percent of (F +
B₂O₃ + P₂O₅) is in the range from 0.8-4.0 and the weight percent of (Li₂O + Na₂O) is in
5 the range from 7-15, and wherein the porcelain comprises
a glassy matrix phase and a leucite crystallite phase, wherein the leucite phase
comprises from about 5 to about 65% by weight of the total composition and the leucite
crystallites have average diameters of less than about 7 microns; and further wherein
the porcelain has a maturing temperature in the range from about 600 °C to
10 about 885 °C and a coefficient of thermal expansion in the range from about 11 to
about 19 x 10⁻⁶/°C (measured from 25 °C to 500 °C).

CLAIM 21. A dental restoration comprising the porcelain of claims 1-20.

CLAIM 22. A method for making a dental porcelain restoration, comprising
forming a dental porcelain powder from a dental composition comprising 40-
65% SiO₂, 6-13% Al₂O₃, 5-15% K₂O, 6-12% Na₂O, 0-3% Li₂O, 0-4% B₂O₃, 0-2% F,
and 0-3% P₂O₅ by weight of the total composition, wherein the weight percent of (F +
5 B₂O₃ + P₂O₅) is in the range from 0.5-4.0 and the weight percent of (Li₂O + Na₂O) is in
the range from 6-15, and wherein the porcelain comprises a glassy matrix phase and a
leucite crystallite phase, wherein the leucite phase comprises from about 5 to about
65% by weight of the total composition and the leucite crystallites have average
diamters of less than about 7 microns; and further wherein the porcelain has a maturing
10 temperature in the range from about 600 °C to about 885 °C and a coefficient of
thermal expansion in the range from about 11 to about 19 x 10⁻⁶/°C (measured from 25
°C to 500 °C);
shaping the dental porcelain powder; and
heating the shaped dental porcelain powder to between about 600 °C to about
15 885 °C to fuse the dental porcelain powder.

-18-

CLAIM 23. The method of claim 22, wherein the dental porcelain powder is fused to a ceramic core or a ceramic or metal framework.

CLAIM 24. A method for making a dental porcelain restoration, comprising
forming a dental porcelain powder from a dental composition comprising 57-
66% SiO_2 , 7-13% Al_2O_3 , 7-18% K_2O , 4-12% Na_2O , 0.5-3% Li_2O , 0-1% B_2O_3 , 0-4% F,
and 0-3% P_2O_5 by weight of the total composition, wherein the weight percent of (F +
5 $\text{B}_2\text{O}_3 + \text{P}_2\text{O}_5$) is in the range from 0.8-4.0 and the weight percent of ($\text{Li}_2\text{O} + \text{Na}_2\text{O}$) is in
the range from 4.5-15, and wherein the porcelain comprises a glassy matrix phase and a
leucite crystallite phase, the leucite phase comprising from about 5 to about 65% by
weight of the total composition and the leucite crystallites having average diamters of
less than about 7 microns; and further wherein the porcelain has a maturing temperature
10 in the range from about 600 °C to about 885 °C and a coefficient of thermal expansion
in the range from about 11 to about $19 \times 10^{-6}/^\circ\text{C}$ (measured from 25 °C to 500 °C);
shaping the dental porcelain powder; and
heating the shaped dental porcelain powder to between about 600 °C to about
885 °C to fuse the dental porcelain powder.

CLAIM 25. The method of claim 24, wherein the dental porcelain powder is fused to a ceramic core or a ceramic or metal framework.

CLAIM 26. The method of claim 24, wherein the powder further comprises
0-1% BaO, 0-3% CaO, 0-7% MgO, 0-5% Cs_2O , 0-1% CeO_2 , and 0-1.0% Sb_2O_3 .

CLAIM 27. The method of claim 26, wherein the composition comprises 62.0%
 SiO_2 , 11.7% Al_2O_3 , 15.8% K_2O , 4.7% Na_2O , 2.6% Li_2O , 0.5% B_2O_3 , 1.7% CaO, 0.8%
MgO, and 0.5% F by weight of the total composition.

-19-

CLAIM 28. A composition for the manufacture of a dental porcelain, comprising a porcelain composition having an increased weight percent of Cs_2O and a molar ratio of $\text{Cs}_2\text{O}/\text{K}_2\text{O}$ of less than 0.1;

5 a coefficient of thermal expansion in the range from about 11 to about $19 \times 10^{-6}/^\circ\text{C}$ (measured from 25°C to 500°C), said coefficient of thermal expansion being comparable to or greater than the same porcelain composition having a lesser weight percent of Cs_2O ; and

a weight percent of leucite lesser than the same porcelain composition having a lesser weight percent of Cs_2O .

CLAIM 29. A method for the manufacture of a leucite-containing porcelain composition, comprising

5 formulating a porcelain composition so as to have an increased weight percent of Cs_2O and a molar ratio of $\text{Cs}_2\text{O}/\text{K}_2\text{O}$ of less than 0.1, thereby resulting in a porcelain composition having

a coefficient of thermal expansion in the range from about 11 to about $19 \times 10^{-6}/^\circ\text{C}$ (measured from 25°C to 500°C), said coefficient of thermal expansion being comparable to or greater than the same porcelain composition having a lesser weight percent of Cs_2O ; and

10 a lesser weight percent of leucite than the same porcelain composition having a lesser weight percent of Cs_2O .

-20-

CLAIM 30. A method for making a low-wear leucite-containing porcelain dental restoration, comprising

determining a desired coefficient of thermal expansion range from about 11 to about $19 \times 10^{-6}/^{\circ}\text{C}$ (measured from 25 $^{\circ}\text{C}$ to 500 $^{\circ}\text{C}$) and maturing temperature in the
5 range from about 600 $^{\circ}\text{C}$ to about 885 $^{\circ}\text{C}$ for the porcelain;

determining a leucite-containing composition which will yield the desired coefficient of thermal expansion and maturing temperature;

modifying the formulation by increasing the weight percent of Cs_2O relative to the initial formulation and maintaining the molar ratio of $\text{Cs}_2\text{O}/\text{K}_2\text{O}$ at less than 0.1,
10 thereby resulting in a porcelain composition having a comparable CTE but less leucite.

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification⁶ : A61K 6/02	A3	(11) International Publication Number: WO 99/45888 (43) International Publication Date: 16 September 1999 (16.09.99)
(21) International Application Number: PCT/US99/05176 (22) International Filing Date: 10 March 1999 (10.03.99) (30) Priority Data: 60/077,378 10 March 1998 (10.03.98) US 60/077,555 11 March 1998 (11.03.98) US 60/088,866 11 June 1998 (11.06.98) US 60/091,527 2 July 1998 (02.07.98) US 09/133,582 13 August 1998 (13.08.98) US (71) Applicant: JENERIC PENTRON INCORPORATED [US/US]; 53 North Plains Industrial Road, Wallingford, CT 06492 (US). (72) Inventors: BRODKIN, Dmitri; 75 Hebert Terrace, West Orange, NJ 07052 (US). PANZERA, Carl; 7 Huntsman Lane, Belle Mead, NJ 08502 (US). PANZERA, Paul; 1 Middleton Drive, Mt. Holly, NJ 08060 (US). PRUDEN, Jana, N.; 70 Dehart Drive, Belle Mead, NJ 08502 (US). KAISER, Lisa; 1201 Holly Court, Monmouth Junction, NJ 08852 (US). BRIGHTLY, Richard; 14 Peachtree Court, South Brunswick, NJ 08852 (US). (74) Agent: REIMER, Leah, M.; Cantor Colburn LLP, 88 Day Hill Road, Windsor, CT 06095 (US).		(81) Designated States: AU, CA, JP, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i> (88) Date of publication of the international search report: 4 November 1999 (04.11.99)
(54) Title: LOW FUSING DENTAL PORCELAINS CONTAINING FINE-GRAINED LEUCITE		
(57) Abstract		
<p>A dental porcelain composition, comprising a glassy matrix and leucite crystallites embedded therein, and having maturing temperatures in the range from about 600 °C to about 885 °C and CTEs in the range from about 11 to about 19, more preferably in the range from about 11.5 to about 18, and most preferably in the range from about 12 to about 17.5 x 10⁻⁶/°C (measured from 25 °C to 500 °C). The tetragonal leucite is preferably both fine-grained (i.e., having average diameters of less than about 7 microns) and uniformly-sized. Preferably, the average diameters are less than about 1 to about 3 microns.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

INTERNATIONAL SEARCH REPORT

Internal Application No
PCT/US 99/05176

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 A61K6/02

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 A61K C04B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 97 30678 A (CERAMCO INC) 28 August 1997 (1997-08-28) page 2, last paragraph -page 5, paragraph 2 page 6, paragraph 2 claims; examples; tables	1-27
X	EP 0 795 311 A (JENERIC PENTRON INC) 17 September 1997 (1997-09-17) page 2, line 1 - line 6 page 2, line 44 -page 5, line 19 claims	1-27
A	EP 0 544 145 A (DEGUSSA ;DUCERA DENTAL GMBH (DE); DUCERA DENTAL GMBH (DE)) 2 June 1993 (1993-06-02) claims; table	1-27
	-/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance
 "E" earlier document but published on or after the international filing date
 "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
 "O" document referring to an oral disclosure, use, exhibition or other means
 "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
 "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
 "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
 "&" document member of the same patent family

Date of the actual completion of the international search

16 September 1999

Date of mailing of the international search report

23/09/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
 NL - 2280 HV Rijswijk
 Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
 Fax: (+31-70) 340-3016

Authorized officer

Cousins-Van Steen, G

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 99/05176

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5 622 551 A (ERBE ERIK M ET AL) 22 April 1997 (1997-04-22) column 3, line 50 -column 4, line 18 column 5, line 21 - line 47 -----	1-27
A	EP 0 272 745 A (AMERICAN THERMOCRAFT CORP) 29 June 1988 (1988-06-29) -----	
A	EP 0 695 726 A (IVOCLAR AG) 7 February 1996 (1996-02-07) -----	

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 99/05176

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9730678 A	28-08-1997	US 5713994 A CA 2233564 A EP 0888107 A	03-02-1998 28-08-1997 07-01-1999
EP 0795311 A	17-09-1997	US 5653791 A AU 1621397 A CA 2199569 A JP 10036137 A	05-08-1997 22-01-1998 12-09-1997 10-02-1998
EP 0544145 A	02-06-1993	DE 4138875 C AT 126428 T BR 9204540 A CA 2083023 A DE 59203294 D DK 544145 T ES 2076651 T GR 3017958 T JP 5194134 A MX 9206752 A US 5346866 A US 5281563 A	17-06-1993 15-09-1995 15-06-1993 28-05-1993 21-09-1995 25-09-1995 01-11-1995 29-02-1996 03-08-1993 01-06-1993 13-09-1994 25-01-1994
US 5622551 A	22-04-1997	WO 9511866 A	04-05-1995
EP 0272745 A	29-06-1988	US 4798536 A AT 75137 T CA 1272222 A DE 3778513 A JP 63287709 A JP 1882859 C JP 6000662 B JP 63265856 A	17-01-1989 15-05-1992 31-07-1990 27-05-1992 24-11-1988 10-11-1994 05-01-1994 02-11-1989
EP 0695726 A	07-02-1996	DE 4428839 A AU 699101 B AU 2722795 A CA 2154990 A US 5618763 A	08-02-1996 19-11-1998 15-02-1996 02-02-1996 08-04-1997

THIS PAGE BLANK (USPTO)